

**TEST REPORT**

**Report No. : MAN:HL:7480003645**

**DATE : 17<sup>th</sup> March, 2016**



**GOYAL INDUSTRIES.**

VILL-FIROJ PUR BANGEI, TAB KBARKBEDA SONIPAT  
HARYANA, SONIPAT-131029  
INDIA

**CONTACT PERSON :** MR. SUNIL GOYAL

**THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED AND IDENTIFIED BY/ON BEHALF OF THE CUSTOMER AS :**

**PRODUCT DESCRIPTION** PLYWOOD  
**COUNTRY OF ORIGIN** INDIA  
**SAMPLE RECD ON** 01/03/2016  
**TESTING PERIOD** 02/03/2016 TO 17/03/2016


Test Requested : Please refer to the result summary.

Test Method & Results : Please refer to next page(s).

Result Summary :

Test Requested	Conclusion
FORMALDEHYDE RELEASE	SEE RESULTS

**Per Pro SGS India Pvt Ltd.**



**Subasini Saraswat**

**Asst. Manager**

Email your Test Report Related Enquiries at [Feedback.HLT@sgs.com](mailto:Feedback.HLT@sgs.com)

**TEST REPORT**

**Report No. : MAN:HL:7480003645**

**DATE : 17<sup>th</sup> March, 2016**



**FORMALDEHYDE RELEASE FROM WOOD BASED PANELS BY GAS ANALYSIS METHOD:**

**TEST METHOD:** With ref. to EN 717-2 :1995

TEST ITEM	RESULT	REPORTING LIMIT
	<b>1</b>	
Moisture Content	7.1	0.5
Formaldehyde Release (Accelerated) (mg/m <sup>2</sup> h)	2.1	0.2

**Sample Description:** 1. PLYWOOD.

**NOTE:**

- % = Percentage by mass
- mg/m<sup>2</sup>h = milligrams formaldehyde per square meter and per hour
- Above test has been subcontracted to SGS overseas lab.

**Remark:** Class E1 requirement : ≤3.5 mg/m<sup>2</sup>h  
 Class E2 requirement : > 3.5 mg/m<sup>2</sup>h To ≤8 mg/m<sup>2</sup>h



\*\*\*\*\* End of Report\*\*\*\*\*